

ADESIVER RE 702

Two-component polyurethane fast adhesive for indoor and outdoor resilient floorings



Description

ADESIVER RE 702 is a two-component polyurethane rapid adhesive with high elasticity and toughness suitable for gluing **indoor and outdoors** the following:

- PVC flooring in rolls or tiles;
- rubber flooring in tiles or sheets;
- rubber sport floorings;
- antishock flooring in tiles or sheets;
- vinyl flooring and textile flooring.

After the complete curing, ADESIVER RE 702 becomes heat, water and weather resistant.

Characteristics

Mixture ratio	10/1
Colour	beige
Application temperature	+10°C ÷ +25°C
Application	notched trowel n. 3-7
Thinning (if necessary)	DILUENTE DMC 50
Pot-Life	45' (1)
Hardening	24 h (1)
Coverage	300-800 g/m ² depending on the subfloor
Storage stability	1 year (2)
Packaging	11 kg (10+1)
Tool cleaning	DILUENTE DMC 50 (with fresh adhesive)

1 at 20°C and 65% R.H.

2 in original sealed containers at temperatures between +10°C and +25°C

Laying conditions

Subfloor

dry, clean, no-dust creating, not too rough.

Humidity of subfloor

- 2,0% max with cement subfloors
- 1,7% max with radiant heating subfloors
- 0,5% max with anhydrite subfloors
- 0,2% max with radiant heating anhydrite subfloors

How to use

It is essential to make sure that there is not a rising damp from the substrate.

Dry but friable substrates must first be primed with suitably diluted PRYMER SF 1105 or PRYMER PUB 77 (see technical data sheets).

Cement substrates with high residual relative humidity should be primed with: PRYMER EPOX WETT, PRYMER WB 328 S, PRYMER SF 1105 and PRYMER PUB 77 (see technical data sheets), sprinkle quartz on the surface and then levelled with RASOCHIM range of products (see technical data sheets).

Poorly absorbent or not-absorbent substrates, remove and clean the surface from dust, grit, glue and waxes residue. Apply by cloth the adhesion promoter DILUENTE APA (see technical data sheet), then apply ADESIVER RE 702. If the surface has to be levelled and smooth, use RASOCHIM range of products (see technical data sheets), after surface preparation with CHIMIGRIP as adhesion promoter (see technical data sheets).

Laying on suitable substrates

Do not dilute ADESIVER RE 702 with alcohol.

Apply the adhesive on the substrate using the suitable notched trowel, working it to incorporate any residual dust.

After final positioning, exert even pressure on the entire surface using suitable rollers to ensure full contact with the adhesive and promote the elimination of any air bubbles.

Note

Always remove the linings to be adhered from their packaging several hours before laying to release tension and stabilize them to room climate conditions.

Rubber flooring can be polluted by plasticizers, waxes and contaminants, it is advisable to prior cleaning with DILUENTE ACETONE.

Label elements

Comp. B

· Suspected of causing cancer.· Harmful if inhaled.· May cause damage to organs through prolonged or repeated exposure.· Causes serious eye irritation.· Causes skin irritation.· May cause respiratory irritation.· May cause respiratory irritation.· May cause allergy or asthma symptoms or breathing difficulties if inhaled.· May cause an allergic skin reaction.

· Contains isocyanates. May produce an allergic reaction.

· Do not handle until all safety precautions have been read and understood.· Wear protective gloves / protective clothing / eye protection / face protection.· IF INHALED: If breathing is difficult, remove victim to fresh air and keep at rest in a position comfortable for breathing.· Store in a well-ventilated place. Keep container tightly closed.

Contents: DIPHENYLMETHANE-4,4'-DIISOCYANATE;



Web link

Be sure to have the latest version of this technical data sheet downloadable also from the following link:



http://www.chimiver.com/tds/EN_ADESIVER_RE_702.pdf