

DILUENTE APA

Adhesion promoter for ceramic surfaces



Description

DILUENTE APA, single-component product formulated with special resins able to improve adhesion of silanes/epoxy/epoxy-polyurethane adhesive and lacquer to glass, enameled, ceramic or metallic surfaces. **Destinations:** Adhesion booster.

Characteristics

| | |
|-------------------------|-----------------------------------------------------------|
| Mixture ratio | single-component |
| Application temperature | +10°C ÷ +25°C |
| Application | cloth |
| Thinning (if necessary) | DILUENTE DS |
| Coverage | 20-40 g/m ² depending on the subfloor and use. |
| Storage stability | 1 year ⁽¹⁾ |
| Packaging | 10 L - 5 L - 1 L |
| Tool cleaning | DILUENTE DS |

1 in original sealed containers at temperatures between +10°C and +25°C

How to use

After having thoroughly cleaned and degreased the surface, rub the subfloor carefully with a cloth soaked in DILUENTE APA and proceed to spread the adhesive/lacquer as soon as the surface is dry. We recommend treating small areas at a time for optimum results. Allow maximum 30 minutes to pass between applying DILUENTE APA and spreading the adhesive.

Label elements

· Highly flammable liquid and vapour. · Causes serious eye damage. · Causes skin irritation. · May cause respiratory irritation. · May cause drowsiness or dizziness.

· Keep away from heat / sparks / open flames / hot surfaces. No smoking. · IF IN EYES: Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do. Continue rinsing. · Wear protective gloves / protective clothing / eye protection / face protection. · Immediately call a POISON CENTER or doctor / physician. · In case of fire: use water to extinguish.

Contents:ALCOL ISOBUTILICO METILETILCHETONE ALCOOL ISOPROPILICO ;



Web link

Be sure to have the latest version of this technical data sheet downloadable also from the following link:



http://www.chimiver.com/tds/EN_DILUENTE_APA.pdf