

Technical Datasheet

Item Code: F306000A | Rev.: 27-08-2026 | Ver: 3.2

FONDO WR 306

Two-component polyurethane primer with high coverage and high solid content



Description

FONDO WR 306 is a two-component polyurethane primer for wooden floors with high coverage and high solid content. FONDO WR 306 has very good sandability allowing two coat lacquering cycles.

Characteristics

Mixture ratio	1/1
Application temperature	+10°C ÷ +25°C
Application	6 mm roller / brush
Thinning (if necessary)	DILUENTE DMC 50
Coverage	100-120 g/m ²
Dust dry	30' ⁽¹⁾
Fingerprint dry	2 h ⁽¹⁾
Pot-Life	1 h 30' ⁽¹⁾
Sanding	12 h ⁽¹⁾
Overcoating without sanding	2-4 h ⁽¹⁾
Wood oxidation	marked
Pore filling	excellent
Storage stability	1 year ⁽²⁾
Packaging	10 L (5+5) - 25 L (12,5+12,5)
Tool cleaning	DILUENTE DNE (with fresh product)

1 at 20°C and 65% H.R.

2 in original sealed containers at temperatures between +10°C and +25°C

How to use

Shake well before use.

FONDO WR 306 catalysed to the indicated ratio and mixed uniformly, has to be applied to wooden floors that have been filled, sanded and carefully vacuumed. After hardening, the surface treated looks glossy due to the high coverage of FONDO WR 306. After 12 hours it is possible to apply, previous sanding with 220 paper grit, one coat of DUROLACK MC 50, STAR 2K, WOOD 2K or TRAFFIK 2K (see technical data sheets).

Label elements

For more information about the safe use of the product it is recommended to consult the latest version of the Safety Data Sheet.

Web link

Be sure to have the latest version of this technical data sheet downloadable also from the following link:



http://www.chimiver.com/tds/EN_FONDO_WR_306.pdf

These information are given from the best of our knowledge and technical experience. They are of general character and not binding in any way our company. Every single case should be put to a practical test by the user who assumes the full responsibility of the final result of his work.